



MIAMI-DADE COUNTY
BUILDING CODE COMPLIANCE OFFICE (BCCO)
PRODUCT CONTROL DIVISION

MIAMI-DADE COUNTY, FLORIDA
METRO-DADE FLAGLER BUILDING
140 WEST FLAGLER STREET, SUITE 1603
MIAMI, FLORIDA 33130-1563
(305) 375-2901 FAX (305) 375-2908

NOTICE OF ACCEPTANCE (NOA)

Tarco
One Information Way
Suite 225
Little Rock, AR 72202

SCOPE:

This NOA is being issued under the applicable rules and regulations governing the use of construction materials. The documentation submitted has been reviewed by Miami-Dade County Product Control Division and accepted by the Board of Rules and Appeals (BORA) to be used in Miami Dade County and other areas where allowed by the Authority Having Jurisdiction (AHJ).

This NOA shall not be valid after the expiration date stated below. The Miami-Dade County Product Control Division (In Miami Dade County) and/or the AHJ (in areas other than Miami Dade County) reserve the right to have this product or material tested for quality assurance purposes. If this product or material fails to perform in the accepted manner, the manufacturer will incur the expense of such testing and the AHJ may immediately revoke, modify, or suspend the use of such product or material within their jurisdiction. BORA reserves the right to revoke this acceptance, if it is determined by Miami-Dade County Product Control Division that this product or material fails to meet the requirements of the applicable building code.

This product is approved as described herein, and has been designed to comply with the Florida Building Code and the High Velocity Hurricane Zone of the Florida Building Code.

DESCRIPTION: Tarco Self-Adhering Modified Bitumen Roofing Systems over Wood Decks

LABELING: Each unit shall bear a permanent label with the manufacturer's name or logo, city, state and following statement: "Miami-Dade County Product Control Approved", unless otherwise noted herein.

RENEWAL of this NOA shall be considered after a renewal application has been filed and there has been no change in the applicable building code negatively affecting the performance of this product.

TERMINATION of this NOA will occur after the expiration date or if there has been a revision or change in the materials, use, and/or manufacture of the product or process. Misuse of this NOA as an endorsement of any product, for sales, advertising or any other purposes shall automatically terminate this NOA. Failure to comply with any section of this NOA shall be cause for termination and removal of NOA.

ADVERTISEMENT: The NOA number preceded by the words Miami-Dade County, Florida, and followed by the expiration date may be displayed in advertising literature. If any portion of the NOA is displayed, then it shall be done in its entirety.

INSPECTION: A copy of this entire NOA shall be provided to the user by the manufacturer or its distributors and shall be available for inspection at the job site at the request of the Building Official.

This NOA consists of pages 1 through 7.

The submitted documentation was reviewed by Jorge L. Acebo.



NOA No.: 07-0917.05
Expiration Date: 11/08/12
Approval Date: 11/08/07
Page 1 of 7

ROOFING SYSTEM APPROVAL

<u>Category:</u>	Roofing
<u>Sub-Category:</u>	Modified Bitumen
<u>Material:</u>	SBS
<u>Deck Type:</u>	Wood
<u>Maximum Design Pressure</u>	-60.0 psf
<u>Fire Classification:</u>	See General Limitation #1

TRADE NAMES OF PRODUCTS MANUFACTURED OR LABELED BY APPLICANT:

TABLE 1

<u>Product</u>	<u>Dimensions</u>	<u>Test Specification</u>	<u>Product Description</u>
EasyLay	3' x 133'4" rolls	ASTM D 226 Type II	Mechanically attached, asphalt coated polyester base sheet.
EasyBase	3' x 72' rolls	ASTM D 6163	Self adhered, fiberglass reinforced, smooth surfaced, SBS modified bitumen base ply membrane.
EasyStick Plus	3' x 36' rolls	ASTM D 6164	Self adhered, polyester reinforced, granule surfaced, SBS modified bitumen cap ply membrane.

APPROVED INSULATIONS:

TABLE 2

<u>Product Name</u>	<u>Product Description</u>	<u>Manufacturer (With Current NOA)</u>
Securock®	Gypsum board	USG
Polyisocyanurate	Polyisocyanurate insulation board	Generic
Expanded & Extruded Polystyrene	Polystyrene roof board insulation	Generic
Wood Fiber	Wood fiber insulation board	Generic
High Density Wood Fiberboard	Wood fiber insulation board	Generic
Perlite Insulation	Perlite insulation board	Generic



APPROVED FASTENERS:

TABLE 3

Fastener Number	Product Name	Product Description	Dimensions	Manufacturer (With Current NOA)
1.	OMG #12, #14 Heavy Duty Fasteners	Roofing and insulation fasteners, with #3 Phillips head.		OMG, Inc.
2.	OMG 3 in. Galvalume Steel Plates	Galvalume steel stress plates.	3" round	OMG, Inc.
3.	Tru-Fast DP	Insulation fastener for wood, steel and concrete		The Tru-Fast Corp.
4.	Tru-Fast HD	Insulation fastener for wood, steel and concrete		The Tru-Fast Corp.
5.	Tru-Fast MP-3	Galvalume steel stress plate	3" round	The Tru-Fast Corp.

EVIDENCE SUBMITTED:

<u>Test Agency</u>	<u>Test Identifier</u>	<u>Test Name/Report</u>	<u>Date</u>
Exterior Research & Design, LLC	T6460.06.07 T6470.08.07-R1	TAS 114(J) ASTM D6163 & D6164	06/26/07 09/06/07



APPROVED ASSEMBLIES

- Membrane Type:** SBS
- Deck Type 1I:** Wood, Insulated
- Deck Description:** 1⁹/₃₂" or greater plywood or wood plank
- System Type C:** All layers of insulation are mechanically attached to roof deck.

All General and System Limitations apply.

One or more layers of the following:

Base Insulation Layer: (Optional)	Insulation Fasteners (Table 3)	Fastener Density/ft²
Any Approved Polyisocyanurate, EPS, Wood Fiberboard Maximum 2" thick	N/A	N/A
Top Insulation Layer	Insulation Fasteners (Table 3)	Fastener Density/ft²
Securock® Minimum 3/8" thick	1,3,4	1:1 ft ²

Note: Base layers of insulation shall be mechanically attached using the fastener density listed. The insulation panels listed are minimum sizes and dimensions; if larger panels are used, the number of fasteners shall be increased maintaining the same fastener density. Please refer to Roofing Application Standard RAS 117 for insulation attachment.

- Base Sheet:** One ply of EasyBase self-adhered.
- Ply Sheet:** (Optional) One ply of EasyBase self-adhered.
- Cap Sheet:** One ply of EasyStick Plus self-adhered.
- Surfacing:** (Optional) Install one of the following to obtain required fire classification.
 1. Gravel or slag at 400 lbs/sq or 300 lbs/sq, respectively, in a flood coat of approved asphalt at 60 lbs/sq.
 2. Karnak 97 Fibrated Aluminum Asphalt Roof Coating or Asbestos Free Aluminum Roof Coating at 1½ gal/sq.
 3. Kokem Products Sunguard Acrylic Roof Coating at 1 gal/sq.
 4. Monsey Endure Aluminum Roof Coating, Weather Check or Pro-Grade Aluminum Roof Coating at 1½ gal/sq.
 5. Grundy al MB Aluminum Roof Coating at 1-2 gal/sq.
 6. Fields F350 Heat Shield Aluminum Coating or F630 Heat Shield Fibered Aluminum Coating at 1½ gal/sq.

Maximum Design Pressure: -52.5 psf (See General Limitation #7)



Membrane Type: SBS
Deck Type 1I: Wood, Insulated
Deck Description: 19/32" or greater plywood or wood plank
System Type D: All layers of insulation and base sheet simultaneously attached.

All General and System Limitations apply.

One or more layers of the following:

Base Insulation Layer: (Optional)	Insulation Fasteners (Table 3)	Fastener Density/ft²
Any Approved Polyisocyanurate, EPS, Wood Fiberboard Maximum 2" thick	N/A	N/A
Top Insulation Layer	Insulation Fasteners (Table 3)	Fastener Density/ft²
Securock® Minimum 3/8" thick	N/A	N/A

Base Sheet: One or more plies of EasyLay, mechanically attached 10" o.c. in the min. 4" lap and 10" o.c. in two, equally spaced, staggered center rows with OMG #12 Heavy Duty fasteners with OMG 3 in. Galvalume Steel.

Ply Sheet: One ply of EasyBase self-adhered.

Cap Sheet: One ply of EasyStick Plus self-adhered.

Surfacing: (Optional) Install one of the following to obtain required fire classification.

1. Gravel or slag at 400 lbs/sq or 300 lbs/sq, respectively, in a flood coat of approved asphalt at 60 lbs/sq.
2. Karnak 97 Fibrated Aluminum Asphalt Roof Coating or Asbestos Free Aluminum Roof Coating at 1½ gal/sq.
3. Kokem Products Sunguard Acrylic Roof Coating at 1 gal/sq.
4. Monsey Endure Aluminum Roof Coating, Weather Check or Pro-Grade Aluminum Roof Coating at 1½ gal/sq.
5. Grundy al MB Aluminum Roof Coating at 1-2 gal/sq.
6. Fields F350 Heat Shield Aluminum Coating or F630 Heat Shield Fibrated Aluminum Coating at 1½ gal/sq.

Maximum Design Pressure: -60.0 psf (See General Limitation #7)



Membrane Type: SBS
Deck Type 1: Wood, Non-insulated
Deck Description: ¹⁹/₃₂" or greater plywood or wood plank
System Type E: Base sheet mechanically fastened.

All General and System Limitations apply.

Base Sheet: One ply of LeakBarrier® EasyLay™ HPP Asphalt Saturated Underlayment fastened to the deck as described below:

Fastening #1: Attach base sheet using 12 ga. annular ring shank nails with min. 32 ga., 1-5/8" diameter tin-caps spaced 7" o.c. in the 4" lap and 7" o.c. in three, equally spaced, staggered center rows.

Fastening #2: Attach base sheet using OMG #12 or #14 Heavy Duty fasteners with OMG 3 in. Galvalume Steel Plate or Tru-Fast DP or HD fasteners with Tru-Fast MP-3 plates spaced 10" o.c. in the min. 4" lap and 10" o.c. in two, equally spaced, staggered center rows

Ply Sheet: One ply of EasyBase self-adhered.

Cap Sheet: One ply of EasyStick Plus self-adhered.

Surfacing: (Optional) Install one of the following to obtain required fire classification.

1. Gravel or slag at 400 lbs/sq or 300 lbs/sq, respectively, in a flood coat of approved asphalt at 60 lbs/sq.
2. Karnak 97 Fibrated Aluminum Asphalt Roof Coating or Asbestos Free Aluminum Roof Coating at 1½ gal/sq.
3. Kokem Products Sunguard Acrylic Roof Coating at 1 gal/sq.
4. Monsey Endure Aluminum Roof Coating, Weather Check or Pro-Grade Aluminum Roof Coating at 1½ gal/sq.
5. Grundy al MB Aluminum Roof Coating at 1-2 gal/sq.
6. Fields F350 Heat Shield Aluminum Coating or F630 Heat Shield Fibered Aluminum Coating at 1½ gal/sq.

Maximum Design Pressure: -60.0 psf (See General Limitation #7)



WOOD DECK SYSTEM LIMITATIONS:

1. A slip sheet is required with Ply 4 and Ply 6 when used as a mechanically fastened base or anchor sheet.

GENERAL LIMITATIONS:

1. Fire classification is not part of this acceptance; refer to a current Approved Roofing Materials Directory for fire ratings of this product.
2. Insulation may be installed in multiple layers. The first layer shall be attached in compliance with Product Control Approval guidelines. All other layers shall be adhered in a full mopping of approved asphalt applied within the EVT range and at a rate of 20-40 lbs./sq., or mechanically attached using the fastening pattern of the top layer
3. All standard panel sizes are acceptable for mechanical attachment. When applied in approved asphalt, panel size shall be 4' x 4' maximum.
4. An overlay and/or recovery board insulation panel is required on all applications over closed cell foam insulations when the base sheet is fully mopped. If no recovery board is used the base sheet shall be applied using spot mopping with approved asphalt, 12" diameter circles, 24" o.c.; or strip mopped 8" ribbons in three rows, one at each side lap and one down the center of the sheet allowing a continuous area of ventilation. Encircling of the strips is not acceptable. A 6" break shall be placed every 12' in each ribbon to allow cross ventilation. Asphalt application of either system shall be at a minimum rate of 12 lbs./sq.
Note: Spot attached systems shall be limited to a maximum design pressure of -45 psf.
5. Fastener spacing for insulation attachment is based on a Minimum Characteristic Force (F') value of 275 lbf., as tested in compliance with Testing Application Standard TAS 105. If the fastener value, as field-tested, are below 275 lbf. insulation attachment shall not be acceptable.
6. Fastener spacing for mechanical attachment of anchor/base sheet or membrane attachment is based on a minimum fastener resistance value in conjunction with the maximum design value listed within a specific system. Should the fastener resistance be less than that required, as determined by the Building Official, a revised fastener spacing, prepared, signed and sealed by a Florida Registered Engineer, Architect, or Registered Roof Consultant may be submitted. Said revised fastener spacing shall utilize the withdrawal resistance value taken from Testing Application Standards TAS 105 and calculations in compliance with Roofing Application Standard RAS 117.
7. Perimeter and corner areas shall comply with the enhanced uplift pressure requirements of these areas. Fastener densities shall be increased for both insulation and base sheet as calculated in compliance with Roofing Application Standard RAS 117. Calculations prepared, signed and sealed by a Florida registered Professional Engineer, Registered Architect, or Registered Roof Consultant **(When this limitation is specifically referred within this NOA, General Limitation #9 will not be applicable.)**
8. All attachment and sizing of perimeter nailers, metal profile, and/or flashing termination designs shall conform to Roofing Application Standard RAS 111 and applicable wind load requirements.
9. The maximum designed pressure limitation listed shall be applicable to all roof pressure zones (i.e. field, perimeters, and corners). Neither rational analysis, nor extrapolation shall be permitted for enhanced fastening at enhanced pressure zones (i.e. perimeters, extended corners and corners). **(When this limitation is specifically referred within this NOA, General Limitation #7 will not be applicable.)**

END OF THIS ACCEPTANCE



NOA No.: 07-0917.05
Expiration Date: 11/08/12
Approval Date: 11/08/07
Page 7 of 7